

Specifica tecnica CORINDONE BIANCO MOTIM MICROGRANE

Granulometrie disponibili

FEPA	Valore max (μm)	Valore medio (μm)	Valore min. (μm)
EKF 230	82,0	$53,0 \pm 3,0$	34,0
EKF 240	70,0	$44,5 \pm 2,0$	28,0
EKF 280	59,0	$36,5 \pm 1,5$	22,0
EKF 320	49,0	$29,2 \pm 1,5$	16,5
EKF 360	40,0	$22,8 \pm 1,5$	12,0
EKF 400	32,0	$17,3 \pm 1,0$	8,0
EKF 500	25,0	$12,8 \pm 1,0$	5,0
EKF 600	19,0	$9,3 \pm 1,0$	3,0
EKF 800	14,0	$6,5 \pm 1,0$	2,0

Composizione Chimica Tipica

Al_2O_3	99,60%
SiO_2	0,05%
Fe_2O_3	0,033%
TiO_2	0,01%
Na_2O	0,30%
CaO + MgO	0,04%

Caratteristiche Fisiche

Densità	$3,9 \text{ g/cm}^3$
Durezza	Mohs 9
Punto di fusione	2040°